

PVC 膜材

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	30x30
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	1050g ± 3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	4300
Tensile Strength at CD	N/5cm	GB/T1040	3650
Tearing Strength at MD	N/5cm	GB/T16578	650
Tearing Strength at CD	N/5cm	GB/T16578	450
Peeling Strength	N/5cm	GB/T3917	夏60 冬70
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1300x1300D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	30x32
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	1200g ± 3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	4350
Tensile Strength at CD	N/5cm	GB/T1040	4100
Tearing Strength at MD	N/5cm	GB/T16578	550
Tearing Strength at CD	N/5cm	GB/T16578	500
Peeling Strength	N/5cm	GB/T3917	夏60 冬70
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional