

PVC 建筑篷房布

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	23x23
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	850g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	3354
Tensile Strength at CD	N/5cm	GB/T1040	2821
Tearing Strength at MD	N/5cm	GB/T16578	312
Tearing Strength at CD	N/5cm	GB/T16578	125
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	23x23
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	850g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	3100
Tensile Strength at CD	N/5cm	GB/T1040	2800
Tearing Strength at MD	N/5cm	GB/T16578	350
Tearing Strength at CD	N/5cm	GB/T16578	260
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	20x20
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	610g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	2900; 3150 (twisting);
Tensile Strength at CD	N/5cm	GB/T1040	2500; 2660 (twisting);
Tearing Strength at MD	N/5cm	GB/T16578	320; 360 (twisting);
Tearing Strength at CD	N/5cm	GB/T16578	260; 150 (twisting);
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	20x20
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	650g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	2900; 3150 (twisting);
Tensile Strength at CD	N/5cm	GB/T1040	2500; 2660 (twisting);
Tearing Strength at MD	N/5cm	GB/T16578	360; 320 (twisting);
Tearing Strength at CD	N/5cm	GB/T16578	260; 150 (twisting);
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	20x20
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	680g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	2900; 3150 (twisting);
Tensile Strength at CD	N/5cm	GB/T1040	2500; 2660 (twisting);
Tearing Strength at MD	N/5cm	GB/T16578	360; 320 (twisting);
Tearing Strength at CD	N/5cm	GB/T16578	260; 150 (twisting);
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	20x20
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	750g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	2900 (不加捻); 3150 (twisting);
Tensile Strength at CD	N/5cm	GB/T1040	2500; 2660 (twisting);
Tearing Strength at MD	N/5cm	GB/T16578	360; 320 (twisting);
Tearing Strength at CD	N/5cm	GB/T16578	260; 150 (twisting);
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	30x30
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	850g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	4300
Tensile Strength at CD	N/5cm	GB/T1040	3650
Tearing Strength at MD	N/5cm	GB/T16578	650
Tearing Strength at CD	N/5cm	GB/T16578	450
Peeling Strength	N/5cm	GB/T3917	夏60 冬70
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		500x500D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	9x9
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	270g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	600 (普纱); 650 (高强)
Tensile Strength at CD	N/5cm	GB/T1040	450 (普纱); 500 (高强)
Tearing Strength at MD	N/5cm	GB/T16578	90 (普纱); 180 (高强)
Tearing Strength at CD	N/5cm	GB/T16578	80 (普纱); 130 (高强)
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		300x500D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	18x12
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	440g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	1300 (普圆); 1300 (高圆)
Tensile Strength at CD	N/5cm	GB/T1040	750 (普圆); 770 (高圆)
Tearing Strength at MD	N/5cm	GB/T16578	140 (普圆); 150 (高圆)
Tearing Strength at CD	N/5cm	GB/T16578	120 (普圆); 130 (高圆)
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		500x500D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	9x9
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	460g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	600 (普纱); 650 (高强)
Tensile Strength at CD	N/5cm	GB/T1040	450 (普纱); 500 (高强)
Tearing Strength at MD	N/5cm	GB/T16578	90 (普纱); 180 (高强)
Tearing Strength at CD	N/5cm	GB/T16578	80 (普纱); 130 (高强)
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Date Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		500x500D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	18x12
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	480g±3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	1300 (普圆); 1300 (高圆)
Tensile Strength at CD	N/5cm	GB/T1040	750 (普圆); 770 (高圆)
Tearing Strength at MD	N/5cm	GB/T16578	140 (普圆); 150 (高圆)
Tearing Strength at CD	N/5cm	GB/T16578	120 (普圆); 130 (高圆)
Peeling Strength	N/5cm	GB/T3917	60 ~80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional