

PVC 篷布 Tarpaulin

Technical Data Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		1000x1000D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	30x30
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	900g ± 3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	4300
Tensile Strength at CD	N/5cm	GB/T1040	3650
Tearing Strength at MD	N/5cm	GB/T16578	650
Tearing Strength at CD	N/5cm	GB/T16578	450
Peeling Strength	N/5cm	GB/T3917	夏60 冬70
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Data Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		500x500D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	18x17
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	480g ± 3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	
Tensile Strength at CD	N/5cm	GB/T1040	
Tearing Strength at MD	N/5cm	GB/T16578	
Tearing Strength at CD	N/5cm	GB/T16578	
Peeling Strength	N/5cm	GB/T3917	
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional

Technical Data Sheet

Properties	Units	Test Method	Average Value
Base Fabric Yarn	D (Denier)		840x840D
Base Fabric Density	线/英寸 (Thread/Inch)	FZ/T01003	18x18
Finished Fabric Weight	克/平方米 (Gram/m ²)	FZ/T01003	500g ± 3%
Thickness	毫米 (mm)	FZ/T01003	/
Tensile Strength at MD	N/5cm	GB/T1040	1800
Tensile Strength at CD	N/5cm	GB/T1040	1550
Tearing Strength at MD	N/5cm	GB/T16578	300
Tearing Strength at CD	N/5cm	GB/T16578	250
Peeling Strength	N/5cm	GB/T3917	60 ~ 80
Temperature Range	℃		-50 ~ +70
Anti-fungal			Optional
Anti-UV			Optional
Frame Retardant			Optional